



Neoprene Flashing Cement

Professional Grade Elastomeric Flashing and Repair Product



Revised: 08/17

- Professional Grade
- Remains Flexible & Watertight
- High Performance Rubberized Elastomeric Cement
- May be Applied in Standing Water for Emergency Repairs
- Meets ASTM D 4586 Type 1 and ASTM D 3409

Manufacturer:

JETCOAT
472 Brehl Avenue
Columbus, Ohio
Phone: 800-394-0047
Fax: 614-279-7201
www.JETCOATinc.com

Description

A high-performance, professional grade elastomeric flashing and repair product that cures to a long lasting rubber-like film. Remains flexible through extreme temperature ranges. Its non-sag property and exceptional adhesion makes this an ideal cement for the construction and repair of flashings, metal joints, seams, coping, vent pipes, skylights and chimneys. Ideally suited for sealing cracks, holes, and tears in built-up roofs and modified bitumen single ply.

Uses

- Splits & Seams
- Vents
- Metal Joints
- Coping
- Flashings
- Skylights
- Chimneys

Surface Preparation

All surfaces to be treated must be free from oil, grease and other foreign materials prior to application. The surface must be firm and free from loose material. On composition roofs, open any breaks or blisters to be patched and permit to dry out before applying this product.

Application

Trim nozzle to desired bead size. Puncture foil at innerbase of nozzle. Using a caulking gun, apply to a minimum wet thickness of 1/4". Allow at least 24 hours to dry (70 °F and less than 50% humidity with no rain) before applying a surface coating. Use above or below grade.

Drying Time

Dries to the touch in 8-24 hours, depending on weather conditions.

Clean Up

- Clean up with waterless hand cleaner immediately after use.

Weather Conditions

- Do not apply if rain is imminent within 24 hours of application.

Coverage (Approximate)

- Coverage will vary with thickness of application but will approximate 30 lineal ft. per cartridge (1/4" thick.)

Precautions

- Do Not Heat or Thin
- Do Not Store Container at Temperatures Above 100 °F
- Combustible. Contains Petroleum Distillate

Safety And Environmental Precautions

- Refer to Material Safety Data Sheet Before Using
- For Exterior Application Only
- Close Container When Not in Use
- Environmental Information is on the Material Safety Data Sheet
- Do Not Reuse Empty Container
- Volatile Organic Content (VOC) is 300 Gm/Liter Max
- Use With Adequate Ventilation
- Keep Out of Reach of Children

This product does not contain any California Proposition 65 Chemicals.

Neoprene Flashing Cement
Professional Grade Elastomeric Flashing and Repair Product

Form No.: JC-TD61439

Packaging

Item #	Container Size	Pack	Weight
61439	10 Oz. Tube	12	11 lbs.

* At time of manufacturing, containers are filled to maximum. However, due to the reduction in volume that occurs after cooling and settling, the actual volume may be less.

Ingredients:	Cas No.
Petroleum Asphalt	8052-42-4
Calcium Carbonate	1317-65-3
Mineral Spirits	64742-88-7
Cellulose Fibers	9004-34-6
Attapulgate Clay	12174-11-7