



Non-Fibered Emulsion Roof and Foundation Coating

Non-Fibered Asphalt Emulsion Coating

- Easy To Apply
- Soap & Water Cleanup
- Seals Out Water & Moisture
- Environmentally Friendly Water-Based Formula
- Zero Voc Formula
- Meets ASTM D 1277, Type III



Manufacturer:

JETCOAT
472 Brehl Avenue
Columbus, Ohio
Phone: 800-394-0047
Fax: 614-279-7201
www.JETCOATinc.com

Description

A non-fibered asphalt emulsion designed for coating a variety of roof surfaces, concrete foundations and wood fences. Non-fibered formulation facilitates ease of sprayability. Environmentally friendly water-based formula. Dries black.

Uses

- Concrete Foundations, Most Roof Surfaces, Wood Fences and Barns

Surface Preparation

When coating roofs, nail down any loose laps or parts. Repair splits, cracks, weak or leaking areas with JETCOAT Plastic Wet or Dry Roof Cement and Asphalt Coated Reinforcing Fabric, adhering to the directions on the container. Brush or broom away all dust, dirt, loose gravel or debris. Remove grease or oil with a detergent and water making sure to thoroughly rinse. Broom away any standing water.

Application

STIR BEFORE AND DURING USE. Coat the entire surface using a brush or suitable spray equipment. Best results are obtained if two coats are applied with the second coat perpendicular to the first. Allow a minimum of 36 hours between coats. Foundation walls should be thoroughly broomed and rinsed with clean water, ensuring the removal of dirt, dust and loose concrete particles. Apply JETCOAT Non Fibered Emulsion Roof and Foundation Coating using a brush or suitable spray

equipment. To reinforce cracks, sandwich a layer of JETCOAT Resin Treated Multipurpose Reinforcing Fabric between subsequent coats. Allow a minimum of 36 hours of curing prior to backfilling.

Drying Time

Allow 24 hours depending on weather conditions.

Clean Up

- While wet, use soap and water.
- When dry, use waterless hand cleaner.

Weather Conditions

- Do not apply if heavy dew or rain is imminent within 24 hours of application.
- Do not apply if temperatures are expected to fall below 50 °F within 24 hours of application.

Coverage (Approximate)

- Metal Surfaces: 75-100 sq. ft. per gallon
- Concrete and Masonry Surfaces: 50-75 sq. ft. per gallon
- Composition Roofing: 50-75 sq. ft. per gallon

Precautions

- Do Not Heat or Thin
- Do Not Freeze
- Do Not Store at Temperatures Below 50 °F
- Do Not Apply Over Coal Tar Surfaces Less Than One Year Old

Safety & Environmental Precautions

- Refer to Material Safety Data Sheet Before Using
- For Exterior Application Only
- Close Container When Not in Use
- Environmental Information is on The Material Safety Data Sheet
- Do Not Reuse Empty Container
- Volatile Organic Content (VOC) is 0 gm/liter max
- KEEP OUT OF REACH OF CHILDREN

Non-Fibered Emulsion Roof and Foundation Coating
Non-Fibered Asphalt Emulsion Coating

Form No.: JC-TD60705

Packaging

Item #	Container Size	Pack	Weight
60705	4.75 Gallon Pail	1	46 lbs.
60701	.9 Gallon Pail	6	55 lbs.

* At time of manufacturing, containers are filled to maximum. However, due to the reduction in volume that occurs after cooling and settling, the actual volume may be less.

Ingredients:	Cas No.
Petroleum Asphalt	8052-42-4
Clay	1332-58-7
Water	7732-18-5
Potassium Bichromate	7778-50-9