



# COOL KING® White Elastomeric Roof Patch

## Acrylic Emulsion Patch Material

- Dries White
- Excellent Adhesion & Flexibility
- Acrylic Formula for Lasting Performance



Revised: 10/11

### Manufacturer:

JETCOAT  
472 Brehl Avenue  
Columbus, Ohio  
Phone: 800-394-0047  
Fax: 614-279-7201  
www.JETCOATinc.com

### Description

An acrylic emulsion patch material designed for repairing cracks, seams, edges around skylights, vents, and metal joints. Dries white.

### Uses

- Cracks
- Seams
- Skylights
- Vents
- Metal Joints

### Surface Preparation

Clean Roof - Sweep off all dirt, dust, and debris. Remove rust, mildew, oil, grease, or other foreign material on the surface. Scrub roof with solution of TSP (Trisodium Phosphate) and water. Remove mold and mildew with bleach solution (1 part chlorine bleach and 3 parts water). Rinse thoroughly and allow to dry.

### Application

**.9 Gallon Pail:** Stir pail thoroughly. With a 4-inch wide paint brush, apply a liberal amount of Elastomeric Roof Patch. Apply Roof Patch 6-inches wide along cracks, seams, or vent areas. Roll Reinforcing Fabric into wet roof patch. Smooth out fabric with paint brush. While material is still wet, brush another coat of Roof Patch over the Reinforcing Fabric. Make certain the fabric is completely embedded into Roof Patch material. Allow Roof Patch material to dry thoroughly before applying White Elastomeric Roof Coating.

**10 Oz. Tube:** Trim nozzle to desired bead size. Puncture foil at innerbase of nozzle. Using a caulking gun, apply to a minimum wet thickness of 1/4". Allow at least 24 hours to dry (70 °F and less than 50% humidity with no rain) before applying a surface coating. Use above or below grade.

### Drying Time

Dependent on depth of repairs. Typically dries within 24 hours.

### Clean Up

Wash tools with water before material dries.

### Weather Conditions

- Application temperature must be a minimum of 60 °F and rising. Do not apply when temperature is expected to drop below 60 °F within a 24 hour period.
- In areas where dew or fog accumulates in the early evening, it is best to coat in the morning. Stop coating by early afternoon (3:00 pm) to prevent wash off, which will occur if dew, fog, or rain arrives before coating dries.
- Do not apply if rain is imminent or forecast within 24 hours of application.

### Coverage (Approximate)

Dependent upon depth and width of areas to be repaired.

### Precautions

- Do Not Thin
- Do Not Freeze
- Do Not Store at Temperatures Below 50 °F

### Safety & Environmental Precautions

- Refer to Material Safety Data Sheet Before Using
- For Exterior Application Only
- Close Container When not in Use

Cool King® White Elastomeric Roof Patch  
Acrylic Emulsion Patch Material

Form No.: JC-TD66221

- Environmental Information Is On The Material Safety Data Sheet
- Do Not Reuse Empty Container
- Volatile Organic Content (VOC) Is 100 gm/liter max
- KEEP OUT OF REACH OF CHILDREN

## Packaging

Item #	Container Size	Pack	Weight
66221	.9 Gallon Pail	6	71 lbs.
66249	10 Oz. Tube	12	11 lbs.

\* At time of manufacturing, containers are filled to maximum. However, due to the reduction in volume that occurs after cooling and settling, the actual volume may be less.

Ingredients:	Cas No.
Water	7732-18-5
Acrylic Emulsion Polymer	Proprietary
Limestone	16389-88-1
Titanium Dioxide	13463-67-7
Ester Alcohol	25265-77-4