



Non-Fibered Fence & Foundation Coating

Asphalt Based Sealer/Preservative

- Penetrates, Preserves & Protects Foundations, Wood Fences, Barns & More
- Use Above or Below Grade
- Meets ASTM D 41



Revised: 07/23

Manufacturer:

JETCOAT
472 Brehl Avenue
Columbus, Ohio
Phone: 800-394-0047
Fax: 614-279-7201
www.JETCOATinc.com

Description

A cold-applied, liquid asphalt in a solvent system ideal for waterproofing above and below grade exterior concrete, masonry walls, and foundations that are completely dry. Dries black. Also may be used as a coating for fences and barns.

Uses

- Concrete Foundations
- Wood Fences & Barns

Surface Preparation

Surface must be clean, dry, and free of moisture both on and beneath the surface.

Application

Stir JETCOAT Non-Fibered Fence and Foundation Coating thoroughly. Apply a single coat over the entire surface with a brush, roller, or airless spray unit.

Drying Time

Up to 24 hours depending on weather conditions and thickness of application.

Clean Up

Clean tools with mineral spirits or waterless hand cleaner before material has dried.

Coverage (Approximate)

- Concrete & Masonry Surfaces: 50-65 sq. ft. per gallon
- Wood or Composition: 65-90 sq. ft. per gallon

Precautions

- Do Not Heat or Thin
- Do Not Store Container at Temperatures Above 100 °F
- Combustible. Contains Petroleum Distillate
- Do Not Use Where Hydrostatic Pressures May be Encountered.
- Do Not Apply Over Coal Tar Surfaces

Safety And Environmental Precautions

- Refer To Material Safety Data Sheet Before Using
- For Exterior Application Only
- Close Container When Not In Use
- Environmental Information Is On The Material Safety Data Sheet
- Do Not Reuse Empty Container
- Volatile Organic Content (VOC) Is 300 Gm/Liter Max
- Use With Adequate Ventilation
- Keep Out Of Reach Of Children



Non-Fibered Fence & Foundation Coating
Asphalt Based Sealer/Preservative

Form No.: JC-TD66525

Packaging

Item #	Container Size	Pack	Weight
66525	4.75 Gallon Pail	1	42 lbs.
66521	.9 Gallon Pail	6	47 lbs.

* At time of manufacturing, containers are filled to maximum. However, due to the reduction in volume that occurs after cooling and settling, the actual volume may be less.

Ingredients:	Cas No.
Petroleum Asphalt	8052-42-4
Mineral Spirits	64742-88-7